

Ethylene – Methyl Acrylate Copolymer

Description

LOTRYL[®] 24MA02 is a random copolymer of ethylene and methyl acrylate produced by high-pressure radical polymerization process.

Applications

Due to the high methyl acrylate content, LOTRYL[®] 24MA02 can be used for applications where softness, flexibility and polarity are required. Typical applications are flexible film, polyesters modification and cable compounds.

Typical properties

Characteristics	Value	Unit	Test Method
Methyl acrylate content	23-26	% Wt	IRTF (internal)
Melt index (190°C / 2.16 kg)	1–3	g/10min	ISO 1133 / ASTM D 1238
Density (23°C)	0.94	g/cm ³	ISO 1183
Melting point	68	°C	ISO 11357-3
Vicat softening point ⁽¹⁾	36	°C	ISO 306 / ASTM D 1525
Tensile modulus ⁽¹⁾	12	MPa	ISO 527 / ASTM D 638
Elongation at break ⁽¹⁾	750	%	ISO 527 / ASTM D 638
Tensile strength at break ⁽¹⁾	9	MPa	ISO 527 / ASTM D 638
Hardness Shore A / D (at 15s) ⁽¹⁾	75 / 22	-	ISO 868 / ASTM D 2240

⁽¹⁾ On compression molded samples

Processing

LOTRYL[®] 24MA02 can be processed with standard polyolefin equipment up to 300°C and it is recommended to purge the equipment after a run is completed.

Storage, handling and safety

LOTRYL[®] 24MA02 should be stored in standard conditions and protected from UV-light. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the LOTRYL[®] 24MA02 is available upon request to your ARKEMA representative or on the web site www.lotryl.com.

August 2010

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



The world is our inspiration

Technical Polymers Division
420, rue d'Estiennes d'Orves
92705 Colombes Cedex - FRANCE
www.arkema.com

www.Lotryl.com