

OREVAC[®] 18360

Maleic anhydride modified Polyethylene

Description

OREVAC[®] 18360 is **anhydride modified polyethylene**. It is available in pellet form for use in conventional extrusion and coextrusion equipment designed to process polyethylene (PE) resins.

Main application

OREVAC[®] 18360 provides outstanding adhesion to PE, EVOH and PA. It is typically used as tie-layer in multilayer structures. It is mainly used in flexible packaging for the production of multilayer barrier films.

Main characteristics

Characteristics	Value	Unit	Test Method
Melt flow index (190 °C – 2.16kg)	2	g/10min	ISO 1133 / ASTM D 1238
Density at 23 °C	0.914	g/cm ³	ISO 1183 / ASTM D 1505
Melting Temperature	120	°C	ARKEMA (DSC)
Vicat	87	°C	ISO 306

Processing

OREVAC® 18360 can be processed over a wide range of conditions.

We suggest using standard Polyolefin working screw.

Conditions typically used in coextrusion with PE and EVOH for the production of blown film :

A standard temperature setting profile would be :

Extruder 200 – 210 – 210 – 210 – 210 °C

Adapter pipe 230 °C

Head 230 °C

Final profile and settings depend on the line and the multilayer structure being run.

Storage

OREVAC® 18360 has to be stocked in dry conditions below 50 °C and protected from UV rays. Improper storage conditions can cause degradation and have consequences on physical properties of the product.

Precautions of use

A safety data sheet as well as information on handling and storage of the **OREVAC® 18360** are available near your correspondent ARKEMA or on the site <http://www.arkema.com/> .

July 2006

The information contained in this document is based on trials carried out by our Research Centers and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.



Technical Polymers Division
4/8, cours Michelet – La Défense 10
92800 Puteaux - France
www.arkemagroup.com

www.orevac.com