

## TECHNICAL DATA SHEET

# RHEOCOAT™ 2121

Rheology modifier for curtain coating

### TYPICAL CHARACTERISTICS

|                              |                                    |
|------------------------------|------------------------------------|
| Nature                       | <b>Anionic polymer in emulsion</b> |
| Appearance                   | <b>Viscous liquid</b>              |
| Solid Content (%)            | <b>37.5</b>                        |
| pH                           | <b>7</b>                           |
| Brookfield viscosity (mPa.s) | <b>300</b>                         |
| Specific gravity             | <b>1.05</b>                        |

### DESCRIPTION

Rheocoat™ 2121 is an anionic polymer allowing a better control of the curtain coating rheology.

### RECOMMENDED ADDITION LEVEL

0.05 to 0.5 as received

### STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC

### HANDLING & STORAGE

Emulsion must be stored inside a building at a constant temperature between 5°C and 30°C. During the storage and handling, the emulsion must not be contaminated by water. Emulsions must be stirred before use as it can separate.

#### Effect of cycles of warm and cold temperatures

The observations are called raincycle. A container of emulsion initially at a temperature of 20°C in a warehouse, is placed, for several hours outside where the temperature is 5°C. The water vapor contained in the free volume above the product condenses and drops of water formed on the roof of the container fall down on the surface of the emulsion, creating local coagulations. Gel formed looks like white stringy lumps floating on the surface or suspended to the cover of the drum or container.

In these conditions, this product should be used within 3 months from delivery.

### PROCESSING INSTRUCTIONS




Shall be introduced at the end of the coating color preparation after the pigments and the binders and prior to the pH adjustment with a diluted caustic soda.

### MARKETS

#### Pulp & Paper

- Coating
  - Paper Coating
- Board Coating
  - Board Coating
  - Rigid Packaging Cardboard
- Paper Coating
  - Paper Coating

### KEY BENEFITS

|  |   |
|--|---|
| • Precoat                              | No  |
| • Topcoat                              | Yes   |
| • Contribution to brookfield viscosity |    |
| • Contribution to high shear viscosity |  |
| • Water retention                      |  |

# RHEOCOAT™ 2121

## HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)