

## TECHNICAL DATA SHEET

# RHEOSPERSE™ 3080

High efficient grinding aid for calcined kaolin clays

### TYPICAL CHARACTERISTICS

Nature	<b>Polycarboxylate in aqueous solution</b>
Appearance	<b>Liquid</b>
Solid Content (%)	<b>45</b>
pH	<b>7</b>
Brookfield viscosity (mPa.s)	<b>900</b>
Specific gravity	<b>1.34</b>

### DESCRIPTION

Rheospense™ 3080 is specially designed for aqueous grinding process of calcined kaolin clays, it can be used on a wide variety of calcined kaolin clays from different deposits. Rheospense™ 3080 provides high-solids stable slurries and therefore contributes to reduce production costs.

### RECOMMENDED ADDITION LEVEL

0.1 to 0.5 % d/d

### STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC

### HANDLING & STORAGE

The product should be protected from the effects of weathering and stored between 5 and 40°C. Once opened, packaging should be resealed immediately after use.

In these conditions, this product should be used within 12 months from delivery.

### HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

### MARKETS

#### Mining & Metallurgy

- Minerals
  - Kaolin

### KEY BENEFITS

- Downstream market
  - Granulometry
  - Suspension stability
  - Type of use
- Paper  
Coarse  
< 6 months  
Grinding

**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**