RHEOSPERSE™

TECHNICAL DATA SHEET

RHEOSPERSE™ 3206

Wet grinding aids for CaCO3

TYPICAL CHARACTERISTICS

Nature	**Polycarboxylate in aqueous solution**
Appearance	**Liquid**
Solid Content (%)	**45**
pH	**8**
Brookfield viscosity (mPa.s)	**450**
Specific gravity	**1.34**

DESCRIPTION

Rheosperse™ 3206 can be used for wet grinding of CaCO3. Rheosperse™ 3206 especially designed for slurries production with coarse to medium particle size.

RECOMMENDED ADDITION LEVEL

0.05 to 1% d/d

STANDARD PACKAGING

Other packaging may be available upon request

- Bulk

HANDLING & STORAGE

The product should be protected from the effects of weathering and stored between 5 and 40°C. Once opened, packaging should be resealed immediately after use.
In these conditions, this product should be used within 12 months from delivery.

HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

MARKETS

Mining & Metallurgy
- Minerals
  - Calcium Carbonate
  - Natural Ground Calcium Carbonate

KEY BENEFITS

• Downstream market	Paper
• Granulometry	Coarse
• Suspension stability	< 6 months
• Type of use	Grinding

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on https://www.arkema.com/global/en/products/product-safety/disclaimer/ which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790
arkema.com

ARKEMA