

## TECHNICAL DATA SHEET

# TOPSPERSE™ CX L

Dispersing agent for paper coating colors

### TYPICAL CHARACTERISTICS

Nature	<b>Sodium polyacrylate</b>
Appearance	<b>Liquid, colour less to slightly yellow</b>
Solid Content (%)	<b>45</b>
pH	<b>8</b>
Brookfield viscosity (mPa.s)	<b>1070</b>
Specific gravity	<b>1.33</b>

### DESCRIPTION

Topsperser™ CX L is an acrylic polymer specially designed for aqueous dispersion of kaolin and calcium carbonate. Topsperser™ CX L provides stable high solids slurries. Topsperser™ CX L contributes to reduce costs and to improve flexibility of Coating Color formulations.

### RECOMMENDED ADDITION LEVEL

0.2 to 0.5 parts d/d

### STANDARD PACKAGING

Other packaging may be available upon request

- 1000L IBC • Bulk

### HANDLING & STORAGE

The product should be protected from the effects of weathering, stored between 5 and 40°C and protected from sun exposure. Once opened, packaging should be resealed immediately after use. In these conditions, this product should be used within 12 months from delivery.

### HEALTH AND ENVIRONMENTAL DATA

For safe handling please refer to the Safety Data Sheet. For more information about health and environmental data, please contact us.

### MARKETS

#### Pulp & Paper

- Coating
  - Paper Coating
- Board Coating
  - Board Coating
- Paper Coating
  - Paper Coating

### KEY BENEFITS

#### MINERALS SUSPENSION

- Clay
- GCC
- PCC
- Talc



#### MINERAL PARTICLE SIZE

- Coarse
- Extrafine
- Fine



**Headquarters: Arkema France**  
51, Esplanade du Général de Gaulle  
92800 Puteaux – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](http://arkema.com)

# ARKEMA