

Plastistrength® 550

Acrylic Process Aid

PRODUCT DESCRIPTION

Plastistrength® 550 process aid is a medium molecular-weight acrylic process aid that brings enhanced processability to most rigid and flexible vinyl compounds such as siding, profile, pipe, calendered sheet, blow-molded bottles, and automotive interior trim parts.

TYPICAL PHYSICAL PROPERTIES

Physical Form	White Powder
Specific Gravity	1.17
Bulk Density	0.45 g/cc
Particle Size	2% Max on 40 Mesh
Percent Volatiles	1.2% Max

PRODUCT BENEFITS

1. Plastistrength® 550 process aid is recommended where enhanced fusion and processability are required.
2. Plastistrength® 550 process aid imparts good hot melt strength to vinyl formulations during processing while minimizing die swell.
3. Plastistrength® 550 process aid has been extensively tested in weatherable applications and is widely used in exterior PVC building products where good weathering performance is critical.

SUGGESTIONS FOR USE

Plastistrength® 550 process aid is recommended for all vinyl applications where better processability and physical properties are desired. Typical uses are window profile, siding, injection-molded articles, calendered sheet, and blow-molded bottles.

Customers should evaluate Plastistrength® 550 process aid in their own laboratories to establish optimum conditions for use in their processes and applications. Arkema's Technical Service Team is available to discuss your application requirements, provide formulation guidance and laboratory testing as needed. Plastistrength® 550 is commonly used in PVC formulations for food or pharmaceutical packaging. Dedicated information on formulation and regulatory status is available upon request.

PACKAGING

Plastistrength® 550 process aid is packaged in 20 kg bags and 500 kg and 1000 lb bulk bags.

STARTING FORMULATION RECOMMENDATIONS

Rigid Bottle	General	
PVC Resin (K-57)	100.0 phr	
Methyl/Octyl Organotin Stabilizer	1.5 - 2.0	
Internal Lubricant	1.5 - 2.0	
External Lubricant	0.1 - 0.2	
Plastistrength® 550 Process Aid	1.5 - 2.0	
Plastistrength® 770 Process Aid	0.5 - 1.0	
Clearstrength® 350 or 320 Impact Modifier	12.0 - 15.0	
Toner	As required	
Rigid Calendered Film and Sheet	General	
PVC Resin (K-60)	100.0 phr	
Methyl/Octyl Organotin Stabilizer	0.6 - 1.5	
Internal Lubricant	1.5 - 2.0	
External Lubricant	0.1 - 0.2	
Plastistrength® 550 Process Aid	1.5 - 2.0	
Plastistrength® 770 Process Aid	0.7 - 1.0	
Clearstrength® 320 Impact Modifier	6.0 - 12.0	
Toner	As required	
Weatherable Profile	NA	Europe
PVC Resin (K65-68)	100 phr	100 phr
Methyl Organotin Stabilizer	1.0 - 1.5	-
Ca/Zn one-pack	-	3.5 - 4.0
Calcium Stearate	1.2 - 1.5	-
Paraffin Wax (165oF)	1.0 - 1.2	-
Plastistrength® 550 Process Aid	0.8 - 1.1	0.5 - 1.1
Plastistrength® 770 Process Aid	0.3 - 0.5	0.0 - 0.5
Durastrength® 200 Impact Modifier	5.0 - 6.0	5.0 - 6.0
Calcium Carbonate (0.7 µm)	0.0 - 5.0	0.0 - 13.0
Titanium Dioxide	9.0 - 10.0	3.5 - 5.5

ENVIRONMENTAL AND SAFETY INFORMATION

BEFORE HANDLING THIS MATERIAL, READ AND UNDERSTAND THE MSDS (MATERIAL SAFETY DATA SHEET) / SDS (SAFETY DATA SHEET) FOR ADDITIONAL INFORMATION ON SAFETY, HEALTH AND ENVIRONMENTAL INFORMATION. The MSDS/SDS are available on our Website www.arkema.com or upon request at our Customer Service Department. Arkema believes strongly in Responsible Care® as a public commitment.

MORE TECHNICAL INFORMATION AVAILABLE

Ask your Arkema account manager for further information on high quality Arkema additives for use in PVC, PC, PBT, ABS, PLA and other polymer systems. Arkema produces a full line of impact modifiers, processing aids and epoxidized vegetable oils. In addition, Arkema's Technical Service staff is also available to assist compounders and processors with formulation and processing advice.

Durastrength® Impact Modifiers

Durastrength® acrylic impact modifiers deliver outstanding impact characteristics for outdoor durable applications in PVC and Engineering Resins.

Plastistrength® Process Aids

Plastistrength® process aids offer producers a complete line of melt strengtheners and metal release agents for PVC and Engineering Resins. Plastistrength® process aids can improve fusion, surging, and aesthetics.

Clearstrength® Impact Modifiers

Clearstrength® MBS impact modifiers are designed for extreme impact or impact/clarity combination in PVC and Engineering Resins.

Biostrength® Additives

Biostrength® product line of impact modifiers, melt strengtheners and metal release agents are designed to improve properties and enhance processability of polylactic acid (PLA) and other biopolymers compounds.

FOR MORE INFORMATION CONTACT

Please contact your local account manager or our headquarters:

In Europe:

ARKEMA
Arkema Coating Resins
420 Rue d'Estienne d'Orves
92705 COLOMBES Cedex, France
Tel: +33 (0) 149 008 080
www.arkema.com/en/products/contact

In US:

Arkema Inc.
Coating Resins
410 Gregson Dr
Cary, NC 27511
Tel: +1 (877) 331-6696
www.arkema.com/en/products/contact

In Asia:

Arkema Pte Ltd.
10, Science Park Road, #01-01A,
The Alpha Singapore Science Park II,
Singapore 117684 Tel: +65 6419 9199
www.arkema.com/en/products/contact

VISIT US AT OUR WEBSITE

www.additives-arkema.com
www.arkema.com

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. The user should thoroughly test any application before commercialization. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement. See SDS for Health & Safety Considerations. Arkema has implemented a Medical Device Policy regarding the use of Arkema products in medical device applications that are in contact with the body or circulating bodily fluids: (<http://www.arkema.com/en/social-responsibility/responsible-product-management/medical-device-policy/index.html>). Arkema has designated Medical grades to be used for such medical device applications. Products that have not been designated as medical grades are not authorized by Arkema for use in medical device applications that are in contact with the body or circulating bodily fluids. In addition, Arkema strictly prohibits the use of any Arkema products in Medical Device applications that are implanted in the body or in contact with bodily fluids or tissues for greater than 30 days.

The Arkema trademarks and the Arkema name shall not be used in conjunction with customers' medical devices, including without limitation, permanent or temporary implantable devices, and customers shall not represent to anyone else, that Arkema allows, endorses or permits the use of Arkema products in such medical devices. It is the sole responsibility of the manufacturer of the medical device to determine the suitability (including biocompatibility) of all raw materials, products and components, including any medical grade Arkema products, in order to ensure that the final end-use product is safe for its end use; performs or functions as intended; and complies with all applicable legal and regulatory requirements (FDA or other national drug agencies) It is the sole responsibility of the manufacturer of the medical device to conduct all necessary tests and inspections and to evaluate the medical device under actual end-use requirements and to adequately advise and warn purchasers, users, and/or learned intermediaries (such as physicians) of pertinent risks and fulfill any postmarket surveillance obligations. Any decision regarding the appropriateness of a particular Arkema material in a particular medical device should be based on the judgment of the manufacturer, seller, the competent authority, and the treating physician.

Clearstrength® and Plastistrength® are registered trademarks of Arkema.
Biostrength® and Durastrength® are registered trademarks of Arkema Inc.
Responsible Care® is a registered trademark of the American Chemistry Council Inc.
2019 Arkema Inc. All rights reserved.